

26

Fe

55.845

Iron

Ni

58.6934

Nickel

Alloy 42

Controlled Expansion Alloys



1. 800.348.6268 | sales@efineametals.com
www.efineametals.com

DESCRIPTION

A controlled expansion alloy consisting of 41% Nickel, balance Iron; used in a wide variety of electronic applications, lead frames, especially for glass and ceramic seals. This alloy is also known as Pernifer[®] 42, NILO[®] 42, Carpenter Glass Sealing[®] 42.

APPLICATIONS

Glass-to-metal seals for a wide variety of electronic tubes, hermetic packages, automotive and industrial lamps.

TYPICAL PHYSICAL PROPERTIES

Density	lb/cu in	0.293
Specific Gravity		8.12
Curie Temp	°F	716
	°C	380
Melting Point	°F	2600
	°C	1425
Electrical Resistivity	ohm-cir mil/ft	430
	Microhms-cm	71
Thermal Conductivity	BTU-in/sq.ft-hr°F	74.5
	W/cm °C	0.11
Specific Heat	BTU / lb °F	0.12

Source: ASTM F30, 42 Alloy | UNS K94100; CarTech Glass Sealing 42 Data Sheet v.7.1.90

FORMS | SIZES AVAILABLE

Plate	0.1875" - 0.410"
Round Bar Rod	0.125" - 6.000"
Sheet	0.020" - 0.125"
Strip Coil	0.010" - 0.080"
Strip Coil Photo-Etch	0.0077" - 0.010"

Listed above are our standard stock items. Our inventory fluctuates based on market demands. If you do not see the size or form you require, please call us.

TYPICAL MECHANICAL PROPERTIES

Tensile Strength	ksi (MPa)	75 (517)
Yield Strength	ksi (MPa)	40 (276)
Elongation	% in 2 in.	30
Hardness Ann.	Rockwell B	76
Modulus of Elasticity	ksi	21.5 x 10 ³

Source: CarTech Glass Sealing 42 Data Sheet v.7.1.90; Material in the annealed condition.

AVERAGE LINEAR COEFFICIENT OF THERMAL EXPANSION $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$

Temperature Range °C	Alloy 42 UNS K94100
30 to 300	4.0 to 4.7*
30 to 400	6.0
30 to 450	6.7 to 7.4*
30 to 500	7.9
30 to 600	9.6
30 to 700	10.5
30 to 800	11.4
30 to 900	12.3
30 to 1000	13.2

Source: ASTM F30, Table X1.1, UNS K94100; *ASTM F30, Table 2

CHEMISTRY %

Nickel 41.0 nom., Bal. Iron
Source: ASTM F30 Table 1; 42 Alloy, UNS K94100



SPECIFICATIONS

ASTM F30 • AMS 1-23011 CL 5 • MIL-1-23011 CL 5 • UNS K94100

New Jersey Offices

769 Susquehanna Avenue, Franklin Lakes, NJ 07417
3 Fir Court, Oakland, NJ 07436

Need pricing? We're here to help:

sales@efineametals.com

1.800.348.6268

California Offices

10537 Humboldt Street, Los Alamitos, CA 90720
1847 W. Business Center Drive, Orange, CA 92867

Special Purpose Alloys & Metals From Stock



1. 800.348.6268 | sales@efineametals.com
www.efineametals.com

JUST-IN-TIME DELIVERY: All of our **standard stock** items can be **shipped within 24-hours** of your order confirmation and most are **shipped the same day**. All materials certified with shipment. For special orders and non-stock materials, contact our sales team for our competitive pricing and delivery lead times.

Controlled Expansion I Glass Sealing

EFINEA supplies the highest quality metals and alloys including materials from Carpenter Technology Corp.

Kovar® I ASTM F15® Alloy

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Kovar®, Pernifer® 2918, NILO K®, DilverP1®

Alloy 42/46/48/52

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Pernifer® 40, 46, 48, 50; NILO® 42, 46, 48, 50;
Glass Sealing 42, 46, 48, 52

Free-Cut Invar "36"® Alloy

Forms: Round Bar/Rod

Invar "36"® Alloy

Forms: Plate, Sheet
Trade Names: Pernifer® 36, NILO® 36, Invar

Super Invar 32-5®

Forms: Plate, Round Bar/Rod, Sheet

Refractory Metals and Alloys

EFINEA is your leading source for quality refractory metals & alloys. We stock DFARS Molybdenum, ML/MLS/MLR, Molybdenum TZM, Tantalum & Tungsten manufactured from Plansee.

Molybdenum

Forms: Plate, Round Bar/Rod, Sheet/Coiled Sheet, Threaded Rod/Nuts, Wire

Molybdenum Lanthanum Oxide (ML)

Forms: Sheet – Stress Relieved, Recrystallized

Molybdenum TZM

Forms: Plate, Round Bar/Rod, Sheet

Niobium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Rhenium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil

Tantalum

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Tungsten

Forms: Plate, Precision Cut Wire, Round Bar/Rod, Sheet

Tungsten Alloys

Forms: Blanks, Flats, Parts, Plate/Sheet, Rod, Shapes

Soft Magnetic Alloys I EMI Shielding & Laminations

EFINEA is a distributor of "EMI shielding alloys" for VDM Metals GmbH the world's leading producer of these alloys.

EFINEA Alloy 50

Forms: Round Bar/Rod, Square Bar, Strip/Coil, Wire Rod
Trade Names: High Permeability 49®, Magnifer® 50

EFINEA Alloy 79

Forms: Rectangular Bar, Round Bar/Rod, Sheet, Strip/Coil

Trade Names: Hipernom, HyMu80

Magnifer® 7904, Molypermalloy, Permalloy 80®

Hiperco® 50

Forms: Strip/Coil

Hiperco® 50A

Forms: Plate, Round Bar/Rod, Strip/Coil

Hiperco® 50 HS

Forms: Strip/Coil

Carpenter VimVar Core Iron

Forms: Round Bar/Rod

Allied pure Iron

Forms: Round Bar/Rod

Electrical & Electronic Nickels

EFINEA supplies select, commercially pure grades of Nickel in various forms and sizes.

Electronic Nickels

200/201/205/233/270

Forms: Round Bar/Rod, Sheet, Strip/Coil, Wire

Copper Metals

EFINEA supplies select, commercially pure grades of Copper available in Coil form.

Copper OFHC 101/102

Nickel-Silver 770

Cupro-Nickel 715 (CuNi 70/30)

Forms: Coil

Alloys and Metals We Distribute

Corrosion Resistant Alloys · High-Temperature Alloys
Stainless Steel · Titanium – CP, 6 Al-4V

EFINEA Services

Slitting, Shearing, Saw Cutting,
Grinding, Water Jet Cutting, Laser Cutting,
Custom Stocking and Consignment Programs



New Jersey Offices

769 Susquehanna Avenue, Franklin Lakes, NJ 07417
3 Fir Court, Oakland, NJ 07436

Need pricing? We're here to help:

sales@efineametals.com
1.800.348.6268

California Offices

10537 Humboldt Street, Los Alamitos, CA 90720
1847 W. Business Center Drive, Orange, CA 92867