

26

Fe

55.845

Iron

28

Ni

58.6934

Nickel

Invar Alloy

Controlled Expansion Alloys



EFINEA

Capabilities Beyond Infinity

1.800.348.6268 | sales@efineametals.com
www.efineametals.com

DESCRIPTION

A low expansion alloy consisting of nominal 36% Nickel, balance Iron. This controlled expansion alloy is known for its rate of thermal expansion that is approximately one-tenth of carbon steel at ambient temperatures up to 400°F. These characteristics have made this alloy a contender for many applications where dimensional changes due to temperature variations must be minimized. Invar is also known under these registered trademarks; Invar 36®, Pernifer® 36, NILO® 36.

APPLICATIONS

Optoelectronics, laser benches, optical benches, electronics and scientific instruments.

TYPICAL PHYSICAL PROPERTIES

Density	lb/cu in	0.291
Specific Gravity		8.05
Curie Temp	°F	535
	°C	279.4
Melting Range	°F	2600
	°C	1427
Electrical Resistivity (70°)	ohm-cir mil/ft	495
	microhm-cm	82.29
Thermal Conductivity	BTU-in/sq.ft-hr °F	72.85
	W/m °C	10
Mean Specific Heat	BTU/lb/ °F	0.123

Source: CarTech Invar 36 Alloy Data Sheet v. 3/15/04

FORMS | SIZES AVAILABLE

Plate	0.250" - 4.50"
Sheet	0.030" - 0.125"

Listed above are our standard stock items. Our inventory fluctuates based on market demands. If you do not see the size or form you require, please call us.

TYPICAL MECHANICAL PROPERTIES*

Tensile Strength	ksi	58 min. - 72.5 max.	
	MPa	400 min. - 500 max.	
Yield Strength	ksi	33.33 min. - 50.7 max.	
	MPa	230 min. - 350 max.	
Elongation	% in 2"	34	
Hardness	Rockwell HRB	B60 min - 85 max.	
Modulus of Elasticity			
	• Annealed Bar & Strip	ksi	20.5 x 10 ³
	• Cold Rolled	ksi	21.5 x 10 ³

Source: ASTM F1684-06 (2021) Table 4 Plate

AVERAGE COEFFICIENT OF THERMAL EXPANSION - μm/m°C

Temperature Range (°C)	UNS NO. K93603, 871 °C 1 hour, Furnace Cool
30 to 100	1.93
30 to 150	2.38
30 to 150	1.2 to 2.7 *
30 to 200	3.03
30 to 250	4.36
30 to 300	6.05
30 to 350	7.51
30 to 400	8.69
30 to 500	10.47
30 to 600	11.75

Source: *ASTM F1684-06 (2021) Table 5; Average linear coefficient range limits; ASTM F1684-06 (2021) Table X2.1

CHEMISTRY %

Nickel 36.0 Nom., Iron Bal.



Need pricing? We're here to help:
sales@efineametals.com
1.800.348.6268

SPECIFICATIONS

ASTM F1684 • AMS I-23011 CL 7 (chemistry only) • MIL- -23011 CL 7 • UNS K93603

New Jersey Offices

769 Susquehanna Avenue, Franklin Lakes, NJ 07417
3 Fir Court, Oakland, NJ 07436

California Offices

10537 Humboldt Street, Los Alamitos, CA 90720
1847 W. Business Center Drive, Orange, CA 92867

Special Purpose Alloys & Metals From Stock



1. 800.348.6268 | sales@efineametals.com
www.efineametals.com

JUST-IN-TIME DELIVERY: All of our **standard stock** items can be **shipped within 24-hours** of your order confirmation and most are **shipped the same day**. All materials certified with shipment. For special orders and non-stock materials, contact our sales team for our competitive pricing and delivery lead times.

Controlled Expansion I Glass Sealing

EFINEA supplies the highest quality metals and alloys including materials from Carpenter Technology Corp.

Kovar® I ASTM F15® Alloy

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Kovar®, Pernifer® 2918, NILO K®, DilverP1®

Alloy 42/46/48/52

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil
Trade Names: Pernifer® 40, 46, 48, 50; NILO® 42, 46, 48, 50;
Glass Sealing 42, 46, 48, 52

Free-Cut Invar "36"® Alloy

Forms: Round Bar/Rod

Invar "36"® Alloy

Forms: Plate, Sheet
Trade Names: Pernifer® 36, NILO® 36, Invar

Super Invar 32-5®

Forms: Plate, Round Bar/Rod, Sheet

Refractory Metals and Alloys

EFINEA is your leading source for quality refractory metals & alloys. We stock DFARS Molybdenum, ML/MLS/MLR, Molybdenum TZM, Tantalum & Tungsten manufactured from Plansee.

Molybdenum

Forms: Plate, Round Bar/Rod, Sheet/Coiled Sheet, Threaded Rod/Nuts, Wire

Molybdenum Lanthanum Oxide (ML)

Forms: Sheet – Stress Relieved, Recrystallized

Molybdenum TZM

Forms: Plate, Round Bar/Rod, Sheet

Niobium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Rhenium

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil

Tantalum

Forms: Plate, Round Bar/Rod, Sheet, Strip/Coil, Wire

Tungsten

Forms: Plate, Precision Cut Wire, Round Bar/Rod, Sheet

Tungsten Alloys

Forms: Blanks, Flats, Parts, Plate/Sheet, Rod, Shapes

Soft Magnetic Alloys I EMI Shielding & Laminations

EFINEA is a distributor of "EMI shielding alloys" for VDM Metals GmbH the world's leading producer of these alloys.

EFINEA Alloy 50

Forms: Round Bar/Rod, Square Bar, Strip/Coil, Wire Rod
Trade Names: High Permeability 49®, Magnifer® 50

EFINEA Alloy 79

Forms: Rectangular Bar, Round Bar/Rod, Sheet, Strip/Coil

Trade Names: Hipernom, HyMu80

Magnifer® 7904, Molypermalloy, Permalloy 80®

Hiperco® 50

Forms: Strip/Coil

Hiperco® 50A

Forms: Plate, Round Bar/Rod, Strip/Coil

Hiperco® 50 HS

Forms: Strip/Coil

Carpenter VimVar Core Iron

Forms: Round Bar/Rod

Allied pure Iron

Forms: Round Bar/Rod

Electrical & Electronic Nickels

EFINEA supplies select, commercially pure grades of Nickel in various forms and sizes.

Electronic Nickels

200/201/205/233/270

Forms: Round Bar/Rod, Sheet, Strip/Coil, Wire

Copper Metals

EFINEA supplies select, commercially pure grades of Copper available in Coil form.

Copper OFHC 101/102

Nickel-Silver 770

Cupro-Nickel 715 (CuNi 70/30)

Forms: Coil

Alloys and Metals We Distribute

Corrosion Resistant Alloys · High-Temperature Alloys
Stainless Steel · Titanium – CP, 6 Al-4V

EFINEA Services

Slitting, Shearing, Saw Cutting,
Grinding, Water Jet Cutting, Laser Cutting,
Custom Stocking and Consignment Programs



New Jersey Offices

769 Susquehanna Avenue, Franklin Lakes, NJ 07417
3 Fir Court, Oakland, NJ 07436

Need pricing? We're here to help:

sales@efineametals.com
1.800.348.6268

California Offices

10537 Humboldt Street, Los Alamitos, CA 90720
1847 W. Business Center Drive, Orange, CA 92867